

## SPECTRAPLAN WALKWAY MEMBRANE

### PRODUCT INFORMATION

TPE walkway membrane with yellow demarcation strips either side  
 Available in 0.76m wide x 15m long rolls  
 Hot air welded to the roof surface in a layout as specified by the client  
 Provides a slip resistant surface and additional protection to the waterproof membrane in areas where mechanical damage is more likely to occur  
 Can be installed over either mechanically fastened or adhered Spectraplan roofing systems

### FEATURES & BENEFITS

- Herringbone Patterned
- Contrasting colour for demarcation
- Excellent UV resistance and durability
- Excellent mechanical properties and product performance
- Efficient and safe installation
- Secure seam welding quality

Description	Spectraplan Walkway Membrane
<b>Thickness</b>	4mm
<b>Width</b>	0.76m
<b>Length</b>	15m
<b>Colour</b>	Dark Grey / Yellow
<b>Material</b>	TPE
<b>Reinforcement</b>	N/A
<b>Product Code</b>	40001576



### INSTALLATION

Before installing the walkway membrane on to the completed roof area thoroughly check the installed Spectraplan membrane for any weak welds, mechanical damage and ensure the area is clean dry and free from any debris or contamination.

If the walkway is to be heavily trafficked or Rockwool thermal insulation board has been used a 0.9mm galvanized steel spreader sheet should be installed either beneath the waterproofing membrane or beneath the walkway membrane. The spreader sheet should be wrapped in IKOtex fleece and each corner fixed to the substrate using suitable IKOfix fasteners.

Unroll the Walkway Membrane, cut to length if necessary and neatly round off any corners.

Hot air weld the Spectraplan Walkway membrane to the Spectraplan membrane beneath carrying out any seam preparation in accordance with the IKO Polymeric Spectraplan installation handbook.

Once the welds have cooled check the weld integrity by using a seam probe or 4mm wide screwdriver (with rounded edges) along the seam applying pressure into the seam. Repair any defects as necessary.

Repeat the process leaving a 25mm gap between each roll end. Do not overlap the Spectraplan Walkway membrane as the grid Pattern may prevent a fully sealed weld being achieved.

## **TYPICAL PROPERTIES**

<b>Characteristic properties</b>	<b>Unit</b>	<b>Method</b>	<b>IKO Spectraplan Walkway</b>
Thickness +10%/- 5%	mm	EN 1849-2	4.0
Length +1%/- 0.5%	m	EN 1848-2	15.00
Width +1%/- 0.5%	m	EN 1848-2	0.76
Minimum Overlap	mm		N/A
Minimum welding width (Automatic)	mm		>30
Minimum welding width (Hand Welder)	mm		>60
Welding temperature	°C		550
Recommended welding speed (Automatic Welder)	m/min		1.5

## **FURTHER PRODUCT INFORMATION**

Full product literature, health & safety and technical sheets are available as downloads from our website [www.ikopolymeric.com](http://www.ikopolymeric.com) or on request by email [polymeric.marketing@iko.com](mailto:polymeric.marketing@iko.com).