


Spectravap Jointing Tape

Product Details

Material	Butyl Tape
Roll Size	19mm x 1.5mm x 30m
Colour	Green
Product Number	30833630



Introduction

- An extruded butyl tape designed for use with Spectravap PE vapour control layer.
- Used in between the overlapped sheets of Spectravap.
- Used for sealing the Spectravap to the building substrate where the VCL terminates to provide an effective air/vapour barrier.
- A high tack tape that remains flexible, ensuring the highest levels of performance.

Features & Benefits

- **Cold Application**
- **Excellent adhesion properties**
- **Fast installation**
- **Cost effective application**

Spectravap Jointing Tape Use

1. Ensure surfaces are clean, dry, and free from frost, grease and other loose materials.
 2. Contaminated substrates should be cleaned with Armourplan Lap Cleaner if necessary and allowed to dry.
 3. Apply direct from the reel on to one surface and consolidate sufficiently along its length to achieve good initial adhesion.
 4. Remove the backing paper and offer the other surface to the jointing tape and push firmly to seal across the joint. The use of a roller to apply firm pressure to the joint is recommended to get a good bond.
- Spectravap Jointing Tape must only be applied in temperatures range of +5°C to +40°C.**

Storage

Spectravap Jointing Tape should be stored flat in dry conditions out of direct sunlight at a temperature between 5°C and 25°C. Shelf life is 24 months when stored in the above conditions.

Typical Properties

Moisture Vapour Transmission Rate	0.16g/m ² /24hr/mm
Dynamic Tensile Adhesion	19 N/cm ²
Dynamic Shear Adhesion	13 N/cm ²
T Peel Adhesion to PE foil	12 N/cm
Specific Gravity	1.6 g/cm ³
Colour	Green
Application Temperature	+5 – +40 °C
Service Temperature	-40 – +90 °C
Shelf Life	24 months

Further Product Information

Full product literature, health & safety and technical sheets are available as downloads from our website www.ikopolymeric.com or on request by email polymeric.marketing@iko.com.



Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.

Company Registered in England No. 2678296 – Registered Office: Appley Lane North, Appley Bridge, Wigan, Lancashire, WN6 9AB

IKO Polymeric

Coney Green Road
Clay Cross, Chesterfield
S45 9HZ

T: 01257 488000

E: polymeric.technical.uk@iko.com

W: www.ikopolymeric.com